



MONOTACK MARMORAPID

Ultra-white rapid-setting mono-component adhesive for marble

CE marking:

- EN 12004-1 - Designation: C2FTES2

Certifications:

- VOC - Decreto francese 321/2011 - Classe: A+



TECHNICAL SPECIFICATIONS



FIELD OF APPLICATION



APPLICATIONS



Description

MONOTACK MARMORAPID is an ultra-white mono-component adhesive for marble and light-coloured natural stone surfaces, made with cement, selected-grain quartz sand, resins and special additives.

MONOTACK MARMORAPID is an adhesive that sets and hardens very rapidly, making it suitable for laying coverings that must be used a few hours after they are applied.

MONOTACK MARMORAPID can be prepared by mixing with the sole addition of clean water when applied. In addition to being highly workable, the product features high adhesiveness and thixotropy, and good open time.

CE marking

- ▶ EN 12004-1 + EN 12004-2

MONOTACK MARMORAPID fulfils the requirements of the EN 12004-1 standard "Adhesives for ceramic tiles - Part 1: Requirements, evaluation and verification of the performance persistence, classification and marking" and of the EN 12004-2 standard "Adhesives for ceramic tiles - Part 2: Test methods", with the following designation:

→ C2FTES2

- Improved (2) cementitious adhesive for laying on floors and walls, in interiors and exteriors.
- Rapid-setting adhesive (F).
- Adhesive with reduced slip (T).
- Adhesive with extended open time (E).
- Highly deformable adhesive (S2).

Certifications

- ▶ VOC - Decreto francese 321/2011 - Classe: A+

MONOTACK MARMORAPID soddisfa i requisiti relativi all'emissione di VOC in ambienti interni, secondo la French Regulation (Decreto n° 2011-321 del 23 marzo 2011 e della Delibera del 19 aprile 2011), rientrando in classe A+ (emissione molto bassa).

Colour

MONOTACK MARMORAPID is available in the following versions:

- ultra-white

Field of application

MONOTACK MARMORAPID is designed for bonding natural or manufactured stone, tiles of any format, ceramic and

MONOTACK MARMORAPID

vitreous mosaics, even on vertical surfaces.

MONOTACK MARMORAPID is a binder specially formulated for laying lithic, ceramic and vitreous coverings of any format, also superimposed, when it is necessary to have a white non-migrating adhesive that ensures quick setting combined with high deformability, for layers up to 15 mm thick.

► MONOTACK MARMORAPID can be used on the following laying supports:

- Interior walls and ceilings coated with cement plaster or painted plaster.
- Plasterboard (rigidly supported).
- Fibre cement walls and cement blocks.
- Exterior walls coated with cement plaster or mortar.
- Ready-made or conventional screeds and self-levelling cement screeds.
- Gypsum, anhydrite screeds, wood, prior treatment with RICRETE 1C.
- Concrete.
- Radiant floors.
- Tiled floors.
- Floors and walls waterproofed with BETONGUAINA and BETONGUAINA.S, NORTIG and other mono-component polymeric systems in dispersion.

► MONOTACK MARMORAPID is suitable for laying:

- Marble, granite and natural stone (silica and carbonate) of all sizes.
- Manufactured stone, with the exception of recompositions with high resin content such as Venetian-style terraces and encapsulations.
- Single-fired and double-fired ceramic tiles.
- Stoneware, porcelain stoneware and clinker tiles of any size.
- Cotto.
- Ceramic and vitreous mosaics on meshes.
- Insulating panels (such as expanded polystyrene, expanded polyurethane, rock wool, glass wool) and sound-absorbing panels type Eraclit®, etc. (point adhesion).

► MONOTACK MARMORAPID is not suitable for bonding on:

- High-shrinkage concrete (such as, for example, thin industrial floors).
- Linoleum and PVC without having first verified the adhesion on the support. In case of a positive outcome, wash the coating with STRIPPER and prime it with RICRETE 1C.
- Rubber floors.
- Galvanised or aluminium sheets.

General preparation of the laying support

- Thoroughly clean the substrate by removing any loose parts, oil, grease, paint and anything else that may prevent proper adhesion; wait for the support to dry before applying the adhesive.
- Verify that new supports have cured correctly: screeds must have terminated their hygrometric shrinkage and plasters must have been made by at least 15 days (for 2 cm thickness).
- To accelerate the curing of a new sand and cement screed, add FAST FLUID 300 to the mix.
- If thin coverings are bonded, the fractionation joints made during the cast can be eliminated with stitching (see technical sheet of BETONGUAINA).
- Any moving cracks must be eliminated through stitching.
- In case of dampness in the support exceeding 5% (measured with the carbide method, ASTM D4944), treat the support with SOLID.
- If the substrate is subject to rising damp, apply Q-PRIMER and Q-RASANTE sprinkled until saturation with 0.3–0.9 mm NATURAL QUARTZ sand and then sand and dedust the surface.
- In case of supports with superficial chalking, consolidate the support with SW SOLID diluted with 5 parts by weight of water.
- In case of supports with evident signs of chalking, even deep down, the day before applying the adhesive, consolidate the surface with NORPHEN FONDO IGRO by sprinkling 0.1–0.6 mm NATURAL QUARTZ on the wet surface.
- In case of bonding on top of old polished floors, the surface should be abraded with a diamond grinding cup.

MONOTACK MARMORAPID

Specific preparation of the laying support

- ▶ To smooth a laying surface IN INTERIORS
 - On the wall, use RASANTE 1100 or 1200.
 - On the floor, use LEVEL FINO for filling thicknesses up to 10 mm.
 - On the floor, use LEVEL HB for filling thicknesses up to 30 mm.
 - On the floor, on sloping surfaces, use GROVE PRIMER ECO and GROVE MASSETTO.
- ▶ To smooth a laying surface IN EXTERIORS
 - On the wall, use RASANTE 2000 2K.
 - On the floor use GROVE PRIMER ECO and GROVE MASSETTO.

Preparing the product

- Pour the mix water (6.25 l/bag) into a suitable service container.
- Add the powder adhesive.
- Mix using a low-speed mixer (500–600 rpm) until obtaining a homogeneous lump-free mixture. • During this phase, the product appears to be very dense, as if it were lacking water: this is normal for MONOTACK MARMORAPID.
- DO NOT ADD WATER and wait 5–7 minutes.
- After 5–7 minutes, mix the mixture again until obtaining a paste of adequate consistency that is ready for being applied.

Application of the product

- ▶ Application of the adhesive
 - For effective wetting of the laying substrate, always apply a thin homogeneous layer of adhesive with the smooth side of the trowel.
 - Apply the desired thickness using a notched trowel suited to the size of the tiles, as explained below.
- ▶ Choice of the trowel and thickness adjustment
 - Mosaics and small formats → TROWEL no. 4
 - Sizes up to (30x30) cm → TROWEL no. 5
 - Large sizes, over (30x30) cm → TROWEL no. 6.
- ▶ Joints
 - Any fractionation joints should be made roughly every 25 m² inside and 10–12 m² outside.
 - For corridors and balconies, consider placing a joint every 6–8 m of length.
 - The structural and expansion joints of the supports must be lined up on the surface.
- ▶ Tiling
 - In very hot summer conditions and when there is dust where the substrate and the back of the tile make contact, wet the surfaces slightly with water.
 - Lay the tiles, applying pressure (even tapping them with a rubber mallet) so that the adhesive wets the entire back part of the tiles and the substrate.
 - Always back-butter tiles larger than 30x30 cm that are subject to heavy loads, immersed in water, laid on radiant floors or outdoors: the mix was nonetheless always wet the entire back surface of the tile.
 - Complete the registration within 30 minutes.
- ▶ Checks on the mix
 - Adverse weather conditions such as beating sunlight, dry wind, high temperatures, etc. and absorbent substrates can lower the open time of MONOTACK MARMORAPID even by a few minutes.
 - In these conditions, continuously check whether the adhesive is still fresh, is able to wet the coating and that no film has formed on the surface: otherwise, mix the product again and re-apply it using the notched trowel. Do not add water to the mix.

Consumption

MONOTACK MARMORAPID

type of application	minimum consumption	maximum consumption	UoM	dilution
All surfaces and materials to be bonded	2	6	kg/m ²	-

Cleaning of tools

- Wet product: clean with water (including a power wash).
- Hardened product: remove mechanically.

Useful application tips

- Do not apply MONOTACK MARMORAPID on supports that are too hot due to the high summer temperatures. In such case, wet the surface with water to cool it and apply the product preferably in the afternoon.
- Do not apply MONOTACK MARMORAPID on frosted surfaces or surfaces that are expected to frost within the next 24 hours after application.
- Do not apply MONOTACK MARMORAPID directly on substrates made with gypsum and anhydrite, but only after first treated them with RICRETE 1C.
- If the area is subject to frequent wetting with water (bathrooms, showers, etc.), coat the substrate with NORTIG 15, NORTIG 15 FIBRATO or BETONGUAINA BASEMENT before applying the adhesive.
- The ideal product for grouting a covering bonded with MONOTACK MARMORAPID is COLORFILL FLEX.

Technical data

► PRODUCT IDENTIFICATION DATA	UoM	value
Consistency	-	powder

► APPLICATION DATA AND FINAL PERFORMANCES	UoM	Value
Mix water	-	25 %
Application temperature	°C	from +5 to +35
Open time, EN 12004-2	min	>30
Operating temperature	°C	from -30 to +90
Registration time	min	30
Minimum curing time for grouting (on wall)	hours	2
Minimum curing time for grouting (on floor)	hours	3
Walk-over time (at +23°C)	hours	3
Minimum commissioning time (at 23°C, 50% R.H.)	hours	24
Minimum commissioning time in continuous immersion	days	3
Density of the mix, EN 1015-6	kg/L	1,65 ± 0,05
Pot-life of the mix	min	30

► TECHNICAL DATA IN CONFORMITY TO EN 12004-1 + EN 12004-2	UoM	value
Initial tensile adhesion at 28 days, EN 12004-2	MPa	3,5 ± 0,1
Transversal deformation, EN 12004-2	-	highly deformable (S2)
Early tensile adhesion (6 hours), EN 12004-2	MPa	0,8 ± 0,1
Tensile adhesion after freeze-thaw cycles, EN 12004-2	MPa	2,6 ± 0,1
Tensile adhesion after immersion in water, EN 12004-2	MPa	2,4 ± 0,1
Tensile adhesion after thermal ageing, EN 12004-2	MPa	3,0 ± 0,1
Fire reaction (Euroclass) for thicknesses below 20 mm, EN 12004-1, Par. 4.4.3	-	E WFT

Storage of the product

- 6 months in the closed original packaging, in a dry and covered place away from direct sunlight, at a temperature between +5°C and +35°C.

MONOTACK MARMORAPID

- Protect the product against humidity.

Packages

VARIANT	PACKAGE	ADR	PACKAGES PER PALLET	COMPONENTS
BIANCO	25 kg bag	NO	48 sacchi	

Legenda ADR:

NO = merce NON PERICOLOSA

LEGAL NOTES

Advice on how to use our products corresponds to the current state of our knowledge and does not involve the assumption of any guarantee and / or responsibility for the final result of the work. They do not refore exempt the customer from the responsibility of verifying the suitability of the products for the use and the prefixed purposes through preventive tests. The website www.nordresine.com contains the latest revision of this datasheet.

EDITION

Issue date: 10.11.2012

Revision: 20.02.2018